

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **09059699 A**

(43) Date of publication of application: **04.03.97**

(51) Int. Cl.

**C11D 17/06**

**C11D 11/00**

(21) Application number: **07215176**

(22) Date of filing: **31.07.95**

(30) Priority: **12.08.94 JP 06211929**  
**15.06.95 JP 07174440**

(71) Applicant: **KAO CORP**

(72) Inventor: **YAMASHITA HIROYUKI**  
**TOYODA KOJI**  
**SAKAGAMI MASAOKI**  
**YAMADA KOJI**  
**KUBOTA TERUO**  
**OGURISU HIROSHI**

**(54) PRODUCTION OF NONIONIC DETERGENT GRANULE**

(57) Abstract:

**PROBLEM TO BE SOLVED:** To obtain nonionic detergent granules having a high bulk density and improved flow characteristics of a powder and caking resistance by granulating a detergent material mixture contg. a nonionic surfactant as the main base material under heating and rolling.

**SOLUTION:** A mixture is prepd. by compounding an org. or inorg. powdery builder which comprises at least one compd. selected from among tripolyphosphates, carbonates, etc., has an average granule size of 500 $\mu$ m or lower, and gives an aq. soln. or dispersion of a concn. of 1g/l having a pH of 8 or higher at 20°C and/or a porous alkaline oil-absorbing carrier with a nonionic surfactant which is a polyoxyethylene alkyl ether formed by the addition reaction of, on average, 5-15mol of ethylene oxide to a 10-20C linear or branched prim. or sec. alcohol and/or an acidic precursor of an anionic surfactant capable of

forming a lamella orientation with an aq. soln. of the nonionic surfactant. The mixture is heated to a temp. high enough to enable the neutralization of at least the acidic precursor compounded and then is granulated under rolling, thus giving nonionic detergent granules having a bulk density of 0.6-1.2g/ml.

COPYRIGHT: (C)1997,JPO